Certificate No.: TC-7922

HEMSHELL
TRANSCENDING BEYOND TESTING

TEST REPORT

ISSUED TO	ASHISH DESAI	ULR No.	tc
SHED NO: 2B, S.NO 1085 ADALAJ, SHERTHA VILLAGE GANDHINAGAR 382424 ,GUJARAT Contact Person : ASHISH DESAI Phone No: 9167255227	**Test Report No.**	HSTD/TR/2610/0014	
	Discipline	Chemical	
	Group	PLASTIC AND RESIN	
	Report Issue Date	15/10/2026	
	Contact Person	15/10/2026	
	Contact Detail	--	
	Email	15/10/2026	

Sample Test Details

Sample receipt Date	15/10/2026	**Sample ID**	HSTD26100036
Analysis starting Date	15/10/2026	**Analysis Completion Date**	15/10/2026
Sample Condition	Ok	**Name of the sample**	chillz Butterscotch laminate
Sample Quantity	1	**Type of Sample**	1
Manufacturing Date	01/01/1970	**Batch No.**	-
Expiry Date	01/01/1970	**Other Details (if any)**	

TEST RESULTS

Sr.No.	Test Parameters	Results	Unit	LOQ	Test Method	Specification
1	Colour migration 40deg for 10days	No colour observed	-	NA	IS 9845-1998 (RA 2020)	-
2	N-Heptane @ 38deg for 30 min	2.65	mg/dm2	NA	IS 9845-1998 (RA 2020)	NMT 10 mg/dm2
3	N-Heptane @38deg for 30 min	26.5	mg/l	NA	IS 9845-1998 (RA 2020)	NMT 60mg/l
Remark/Note:	Sample complies as per specification					

REVIEWED BY
Bency Joseph
(Quality Manager lab)

AUTHORIZED SIGNATORY
Bency Joseph
(null)

******* END OF THE TEST REPORT *******

1. The result listed refer only to the tested samples(s) and applicable parameter(s). 2. In Case Sampling is not done by Laboratory ,the results apply to the sample as received. 3. There are no additions to, deviations or exclusions from the method. 4. The report shall not be reproduced except in full, without written approval of the laboratory. 5. Laboratory is not responsible for the authenticity of photocopied test report. 6. Please see Embossed seal to confirm the authenticity of this report. Disclaimer: Information is supplied by the customer(s) and can affect the validity of results.

HS/QP/64/FO3

HEMSHELL SERVICES – CT & T Centre
903/1, Makarpura, GIDC Estate, Makarpura, Vadodara - 390010 Gujarat - India.
Phone: +91 265 2631053 / 2646999, Telefax: +91 022 26860692
Email: support@hemshellservices.com
www.hemshellservices.com, www.hemeteck.com